

Table 1

Composition	Example 1	Example 2	Example 3	Comparative Example 1	Comparative Example 2
SIB	100	100	100		
SIBS	30			100	
IIR					100
SEPS		20			
EOC			20		
Tackifying resin	50	40	40	50	50
Plasticizer	5	5	5	5	5
Silane coupling agent	4	4	4	4	4
Water vapor permeability g/m ² ·24hr	3.0	4.5	3.5	3.0	2.8
Tackiness to glass	Good	Good	Good	Not good	Good
Shape retention property	Good	Good	Good	Good	Not good